



# TriStitch® Jumpsuit

ITEM #S	OJS-[size], 24212-[size], 24217-[size], 24218-[size], 24219-[size], 24220-[size], 24221-[size], 24223-[size], 24225-[size], 24226-[size], 24227-[size]
DESCRIPTION	TriStitch® Jumpsuit
SIZES	S-10XL
MATERIALS	65% polyester, 35% cotton twill
COLORS	Orange (OJS), Chocolate Brown (24221), Green (24220), Hot Pink (24226), Khaki (24218), Lime Green (24227), Medium Gray (24225), Navy (24212), Red (24217), Yellow (24223), White (24219)
CONSTRUCTION	<ul style="list-style-type: none"> <li>• Raglan short sleeves</li> <li>• Elasticized waistband: 26-gauge, heavy duty elastic</li> <li>• Hemmed sleeves and bottoms</li> <li>• 6 solid brass, nickel plated snaps</li> <li>• One double needle stitched breast pocket</li> <li>• Color-coded woven size label</li> <li>• Reinforcing bar tacks at stress points</li> <li>• Hems are 1/2in wide, double folded and are finished with overlapping circular stitching</li> </ul>
STITCHING	3-needle felling stitch on all seams for maximum strength and durability
THREAD	Tex Size T-40, D-Core or equivalent thread is used on all interior and exterior seams and is color matched to the garment
TREATMENTS	IronClad® finish – includes CRF treatment [Crease & Soil Resistant)
PACKAGING	All garments are individually packaged in poly bags
WEIGHT	Fabric: 7.5 oz per yd
CARE INSTRUCTIONS	Wash warm and tumble dry. Stands up to the bleach levels recommended for industrial laundries with minimal shade loss.
DIFFERENTIATORS	CTPAT certified manufacturing
CASE PACK	EA
OTHER	<ul style="list-style-type: none"> <li>• Screen printed size label for easy sorting</li> </ul>

**NOTES****Other Fabric Specifications**

Warp is the scrim running the length of the fabric

Fill is the scrim running the width of the fabric

Strength Type	Warp	Fill
Tear	14 lbs	12 lbs
Tensile	175-200 lbs	130-150 lbs

**Other Thread Specifications**

Tex is the thread (yarn) size

This is the unit for expressing linear density,  
equal to the weight in grams of 1 kilometer of yarn

Tex Size	T-40	
Strength	4.13 lbs	Avg single-end break
Elongation	20.6%	Avg elongation at break
Shrinkage	<1%	At 212°F (boiling water)
Hot Air Shrinkage	<2%	
Loop Strength	5.65 lbs	Avg loop break strength
Loop Strength Ratio	1.3	
Seam Strength	46.3	Lockstitch [8 spi)